

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

This Page Blank (uspto)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 11/00, 11/02, C09C 1/56	A1	(11) International Publication Number: WO 97/47698 (43) International Publication Date: 18 December 1997 (18.12.97)
(21) International Application Number: PCT/US97/08854 (22) International Filing Date: 5 June 1997 (05.06.97) (30) Priority Data: 08/663,693 14 June 1996 (14.06.96) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: MAHMUD, Khaled; 7 Lynne Avenue, Tyngsboro, MA 01879 (US). BELMONT, James, A.; 8 Conant Street, Acton, MA 01720 (US). ADAMS, Curtis, E.; 11 Lovell Road, Watertown, MA 02172 (US). FOSTER, John, K.; 35 Castle Hill Road, Windham, NH 03087 (US). (74) Agent: CAIRNS, James, A.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: INK AND COATING COMPOSITIONS CONTAINING SILICON-TREATED CARBON BLACK (57) Abstract Ink and coating compositions are disclosed comprising a silicon-treated carbon black. The silicon-treated carbon black may have at least one attached organic group, and the ink and coating compositions may comprise a combination of silicon-treated carbon black products, with and/or without at least one attached organic group, and untreated carbon black. Methods are disclosed for improving the jetness, improving the blue tone, improving the platewear, reducing the premix residue, modifying rheological properties, or improving waterfastness, of ink and coating compositions by incorporating therein silicon-treated carbon black.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INK AND COATING COMPOSITIONS CONTAINING
SILICON-TREATED CARBON BLACK

BACKGROUND OF THE INVENTION

5. Field of the Invention

This invention relates to ink and coating compositions containing silicon-treated carbon black.

Discussion of the Related Art

10 Inks are colored liquids or pastes formulated to transfer an image. Pigments such as carbon black are used to impart desired properties to an ink system. Desired properties of inks include visual characteristics such as jetness, opacity, and blue tone. Other performance characteristics include appropriate rheological properties, waterfastness and permanence. For economic reasons, it is desirable to have a pigment that readily disperses in the ink formulation. The measure of the rate of dispersion is the premix residue. Properties such as premix residue thus have a significant influence on the economics of ink production.

15 Coatings are used for decorative, protective and functional treatments of many kinds of surfaces. Pigments are also commonly used in coatings to impart desired properties. Desired properties similarly may include jetness, opacity, and blue tone, as well as appropriate rheological properties. As in inks, for economic reasons, it is desirable to have a pigment that readily disperses in the coating formulation. Some coatings, such as those on undersea pipelines, are for protective purposes. Others, such as exterior
20 automobile coatings, fulfill both decorative and protective functions. Still others provide friction control on boat decks or car seats.

There remains a need for improved ink and coating compositions available for use in a variety of applications.

SUMMARY OF THE INVENTION

25. The present invention relates to ink and coating compositions comprising a silicon-treated carbon black. The silicon-treated carbon black may have at least one attached organic group. The present invention also relates to ink and coating compositions comprising a combination of silicon-treated carbon black products, with and/or without at least one attached organic group, and untreated carbon black. The present invention further relates to methods for: improving the jetness, improving the blue tone,

improving the platewear, reducing the premix residue, modifying rheological properties, or improving waterfastness, of ink and coating compositions by incorporating therein silicon-treated carbon black.

Both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the invention as claimed.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to ink and coating compositions comprising silicon-treated carbon black.

The ink and coating compositions of the present invention may comprise a silicon-treated carbon black. The silicon-treated carbon black may have no attached organic group or may have at least one attached organic group; or it may comprise both silicon-treated carbon black having at least one attached organic group and silicon-treated carbon black having no attached organic group. Untreated carbon black may be combined with either type of silicon-treated carbon black, or with a mixture of both types of silicon-treated carbon black. "Untreated carbon black" is carbon black that has not been treated with silicon. "Untreated carbon black" may be completely untreated, may have one or more attached organic groups, or may have been otherwise treated.

The ink and coating compositions of the invention advantageously provide an improvement in one or more of jetness, blue tone, platewear, premix residue, rheological properties, and waterfastness

The silicon-treated carbon black of the ink or coating of the present invention typically contains from about 0.1 to about 25 weight % silicon, based on the weight of the silicon-treated carbon black.

Preferably, the silicon-treated carbon black contains from about 0.2 weight % to about 10 weight % silicon, and more preferably about 0.2 to about 5.4 weight %, based on the weight of the silicon-treated carbon black.

Typically, the silicon-treated carbon black may be present in the ink or coating in amounts up to about 60 % by weight, based on the weight of the ink or coating. Preferably the silicon-treated carbon black is present between about 10 and about 25% by weight for finished inks and between about 2 and about 25% by weight for coatings. In both inks and coatings, it is not unusual to disperse the carbon black at a higher loading and then reduce it to the final desired loading after the dispersion step.

The ink and coating compositions of the present invention may be aqueous or non-aqueous, and the ink compositions may be used in ink jet applications. Aqueous includes mixtures of water and other water-miscible or -dispersible substances, such as alcohol. The ink and coating compositions of the present invention may exhibit unique rheological properties, depending on whether the compositions are aqueous or nonequeous and on the particular base used in the composition.

The ink compositions of the invention may further optionally include resins/polymers, additives, fillers and/or diluents.

When used, ink composition ingredients such as those listed above are weighed, and mixed and ground together or separately, according to desired formulas.

The ink compositions of the invention are useful in, by way of example, printing inks, ultraviolet cure inks, ball point inks, stamp pad inks, and inks for other applications. McGraw-Hill's Encyclopedia of Science and Technology, 6th Edition, Vol. 9, pages 171-176, provides further details of the types of inks available and their uses, all of which is incorporated herein by reference.

For a general discussion on the properties, preparation and uses of aqueous inks, see, The Printing Manual, 5th Ed., Leach et al., Eds. Chapman and Hall, 1993, incorporated herein by reference. Various aqueous ink compositions are also disclosed, for example, in United States Patent Nos. 2,833,736, 3,607,813, 4,104,833, 4,308,061, 4,770,706 and 5,026,755, the disclosures of which are incorporated herein by reference.

Non-aqueous inks are used for many applications where aqueous vehicles are not suitable. For instance, inks which are to be printed on hydrophobic, non-porous substrates such as glass, metal or plastics must be fast drying. Therefore, solvents such as ketones, esters, alcohols or hydrocarbons are often used instead of water. Such solvent based inks are used widely for industrial labeling of cardboard boxes and various metal or plastic containers and components.

One common type of non-aqueous ink is newsink. A typical newsink can be made in two stages. First, a pigment, e.g., the silicon-treated carbon black of the present invention, and a vehicle are mixed to form a 'premix', and the premix is then milled to achieve optimum dispersion of the pigment.

-4-

Generally, lower premix residues result in faster or improved dispersion, which results in improved economy for the producer.

Flow properties of ink at low shear rates are affected by the dispersion characteristics of the ink's pigments. Depending on the application, different levels of flow are desirable. In screen printing inks, it is desirable to have inks with short flow so that the inks do not flow through the screen prematurely. In offset printing, longer flows may be desirable as the ink travels over the inking rollers. Rheological additives are often added to adjust such flows.

Ink jet printing is a non-impact process wherein droplets of ink are produced and deposited on a substrate such as paper, transparent film, or textile material in response to an electrical signal. Conventional inks for ink jet printers comprise a colorant such as a dye which is soluble in the ink vehicle. Dyes have several disadvantages when used in ink jets, however. Dyes may redissolve in water, dye images smear or rub off on contact with felt pen markers, and dyes exhibit poor light stability. Pigments used as colorants in ink jet inks offer superior properties in such areas as waterfastness, lightfastness, image density and thermal stability. The silicon-treated carbon black pigment must be dispersed and stabilized in the ink jet ink so that properties such as ejectability, print quality, and optical density are not detrimentally affected.

The coating compositions of the invention include silicon-treated carbon black pigment, a solvent, and, optionally, one or more ingredients selected from binders, for example, resins or polymers, and other various additives. Coatings can be manufactured and applied as liquids and are converted to "solid" films after application to the substrate. Coatings are used for decorative, protective and functional treatments of many kinds of surfaces. These surfaces include coils, metals, appliances, furniture, hardboard, lumber and plywood, marine, maintenance, automobiles, cans and paperboard.

As mentioned above, the ink and coating compositions of the present invention may comprise any of a number of additives.

For instance, in an ink composition for use as an ink jet ink, a humectant may be added to reduce the rate of evaporation of water in an ink composition to minimize printhead nozzle clogging in

ink jet applications, for example. If the ink begins to dry out, the humectant concentration increases and evaporation decreases further.

Humectants may also affect other properties of inks and coatings, such as viscosity, pH, surface tension, optical density, and print quality. Preferred humectants include ethylene glycol, propylene glycol, diethylene glycols, glycerine, dipropylene glycols, polyethylene glycols, polypropylene glycols, amides, ethers, carboxylic acids, esters, alcohols, organosulfides, organosulfoxides, sulfones, alcohol derivatives, carbitol, butyl carbitol, cellosolve, ether derivatives, amino alcohols, and ketones.

Biocides such as benzoate or sorbate salts may be important in aqueous inks and coatings to prevent bacterial growth.

Binders that attach to the substrate to hold the colorant on the substrate may be added in a variety of ink and coating compositions. Examples include polyester, polyester-melanine, styrene-acrylic acid copolymers, styrene-acrylic acid-alkyl acrylate copolymers, styrene-maleic acid copolymers, styrene-maleic acid-alkyl acrylate copolymers, styrene-methacrylic acid copolymers, styrene-methacrylic acid-alkyl acrylate copolymers, styrene-maleic half ester copolymers, vinyl naphthalene-acrylic acid copolymers, vinyl naphthalene-maleic acid copolymers, and salts thereof. Drying accelerating agents promote evaporation once the ink or coating is placed on the substrate. These include sodium lauryl sulfate, N,N-diethyl-m-toluamide, cyclohexylpyrrolidinone, and butyl carbitol. Penetrants such as alcohols, sodium lauryl sulfate, esters, and ketones allow an ink to penetrate the surface of the paper. Alcohols may also be used to increase the rate of drying of the liquid ink or coating.

And surfactants like detergents and soap reduce the surface tension to allow the ink or coating to spread on the substrate.

The ink and coating compositions of the present invention may be prepared utilizing conventional techniques. Specifically, milling, such as steelshot milling or three-roll mixing, may be employed to obtain good dispersion of the silicon-treated carbon black in the composition.

The silicon-treated carbon black pigment of the present invention may be obtained by manufacturing the carbon black in the presence of volatilizable silicon-containing compounds. A full description of such a manufacturing process is found in U.S. patent application serial no. 08/446,142

for "Elastomeric Compounds Incorporating Silicon-treated Carbon Blacks and Coupling Agents," and U.S. patent application serial no. 08/446,141 for "Elastomeric Compounds Incorporating Silicon-treated Carbon Blacks," the disclosures of which are fully incorporated herein by reference. The silicon-treated carbon blacks are preferably produced in a modular or "staged" furnace carbon black reactor. Hot combustion gases are generated by contacting a liquid or gaseous fuel with a suitable oxidant stream such as air, oxygen, or mixtures of air and oxygen. Among the fuels suitable for use in contacting the oxidant stream are any readily combustible gas, vapor or liquid streams such as natural gas, hydrogen, methane, acetylene, alcohols, or kerosene. It is generally preferred, however, to use fuels having a high content of carbon-containing components and in particular, hydrocarbons. The ratio of air to fuel varies with the type of fuel utilized. When natural gas is used to produce the carbon blacks of the present invention, the ratio of air to fuel may be from about 10:1 to about 1000:1 by volume. To facilitate the generation of hot combustion gases, the oxidant stream may be pre-heated.

Carbon black feedstock is injected into the gas stream at a point downstream of the flow. Preferred carbon black feedstocks include petroleum refinery sources such as decanted oils from catalytic cracking operations, as well as the by-products from coking operations and olefin manufacturing operations. In the reaction zone portion of the reactor, the feedstock is pyrolyzed to carbon black. The reaction is arrested in a quench zone of the reactor, the quench serving to cool the carbon black particles, reduce the temperature of gaseous stream, and decrease the reaction rate. Optionally, quenching may be staged, or take place at several points in the reactor. After the carbon black is quenched, the cooled gases and carbon black pass downstream into any conventional cooling and separating means whereby the carbon black is recovered. The separation of the carbon black from the gas stream is readily accomplished by conventional means such as a precipitator, cyclone separator, bag filter, or other means known to those skilled in the art. After the carbon black has been separated from the gas stream, it is optionally subjected to a pelletization step.

The silicon-treated carbon blacks of the present invention may be produced by introducing a volatilizable silicon-containing compound into the carbon black reactor at a point upstream of the quench zone. Useful volatilizable compounds include any compound that is volatilizable at carbon black reactor

-7-

temperatures. Examples include, but are not limited to, silicates such as tetraethoxy orthosilicate (TEOS), tetramethoxy orthosilicate, and the like; silanes such as tetrachloro silane, trichloro methylsilane, and the like; and volatile silicone polymers such as octamethylcyclotetrasiloxane (OMTS) and the like. The flow rate of the volatilizable compound will determine the weight percent of silicon
5 in the treated carbon black.

The volatilizable compound may be premixed with the carbon black-forming feedstock and introduced with the feedstock into the reaction zone. Alternatively, the volatilizable compound may be introduced to the reaction zone separately from the feedstock injection point. Such introduction may be upstream or downstream from the feedstock injection point, provided the volatilizable compound is
10 introduced upstream from the quench zone. Upon volatilization and exposure to high temperatures in the reactor, the compound decomposes, and reacts with other species in the reaction zone, yielding silicon-treated carbon black, such that the silicon, or the silicon-containing species, becomes an intrinsic part of the carbon black. If the volatilizable compound is introduced substantially simultaneously with the feedstock, the silicon-treated regions are distributed throughout at least a portion of the carbon black
15 aggregate. The volatilizable compound may alternatively be introduced to the reaction zone at a point after carbon black formation has commenced but before it has been subjected to the quench. In this case, silicon-treated carbon black aggregates are obtained in which silicon or a silicon-containing species is present primarily at or near the surface of the carbon black aggregate. Besides volatilizable compounds, decomposable compounds that are not necessarily volatilizable can also be used to yield the
20 silicon-treated carbon blacks. In addition, carbon black coated with silica as described in U.S. patent application serial no. 08/446,140 for "Elastomeric Compounds Incorporating Partially Coated Carbon Blacks," the disclosure of which is herein incorporated by reference, may also be used in the ink and coating compositions of the present invention.

In the silicon-treated carbon black of the present invention, silicon or a silicon-containing species,
25 including but not limited to, silicon oxides, e.g., SiO_2 , and silicon carbides, may be distributed through at least a portion of the carbon black aggregate as an intrinsic part of the carbon black. Silicon-treated carbon black aggregates of the present invention are not a mixture of discrete carbon black aggregates

and discrete silica aggregates, but include at least one silicon-containing region either at the surface of or within the carbon black aggregate. When the silicon-treated carbon black is examined under STEM-EDX (Scanning Transmission Electron Microscope - Energy Dispersive X-ray), the silicon signal corresponding to the silicon-containing species is found to be present in individual carbon black aggregates. By comparison, in a physical mixture of silica and carbon black, STEM-EDX examination reveals distinctly separate silica and carbon black aggregates.

An alternative way to describe the silicon-treated carbon black aggregate is an aggregate comprising a carbon phase and a silicon-containing species phase. The aggregate, thus contains at least two phases, one of which is carbon and the other of which is a silicon-containing species. The silicon-containing species that is part of the aggregate is not attached to a carbon black aggregate like a silica coupling agent, but actually is part of the same aggregate as the carbon phase. The details of making the silicon-treated carbon black are further explained in U.S. Patent Application Serial Nos.: 08/446,141, filed May 22, 1995; 08/446,142, filed May 22, 1995; 08/528,895, filed September 15, 1995; and 08/750,017, filed November 22, 1996, which is a National Phase Application of PCT No. WO 96/37547, filed May 21, 1996. All of these patents and applications are incorporated in their entireties herein by reference.

Optionally, the silicon-treated carbon blacks of the present invention may have at least one organic group attached. Such carbon blacks can be prepared, for example, based on the disclosures in U.S. patent application serial no. 08/356,660, filed December 15, 1994, and its continuation-in-part application, serial no. 08/572,525, filed December 14, 1995, the disclosures of which are fully incorporated by reference herein. The organic group or groups are preferably attached to the silicon-treated carbon black in accordance with the methods disclosed in the above applications.

The organic group may be an aliphatic group, a cyclic organic group, or an organic compound having an aliphatic portion and a cyclic portion. The organic group may be substituted or unsubstituted, branched or unbranched. Aliphatic groups include, for example, groups derived from alkanes, alkenes, alcohols, ethers, aldehydes, ketones, carboxylic acids, and carbohydrates. Cyclic organic groups include, but are not limited to alicyclic hydrocarbon groups (for example, cycloalkyls, cycloalkenyls),

heterocyclic hydrocarbon groups (for example, pyrrolidinyl, pyrrolinyl, piperidinyl, morpholinyl, and the like), aryl groups (for example, phenyl, naphthyl, anthracenyl, and the like), and heteroaryl groups (imidazolyl, pyrazolyl, pyridinyl, thienyl, thiazolyl, furyl, triazinyl, indolyl, and the like).

When the organic group is substituted, it may contain any functional group compatible with the formation of a diazonium salt. Functional groups include, but are not limited to, R, OR, COR, COOR, OCOR, halogen, CN, NR_2 , $\text{SO}_2\text{NR}(\text{COR})$, SO_2NR_2 , $\text{NR}(\text{COR})$, CONR_2 , NO_2 , SO_3M (where M is H, Li, Na, Cs, or K), SO_3NR_4 , and $\text{N}=\text{NR}'$. R is independently hydrogen, $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl (branched or unbranched), $\text{C}_2\text{-C}_{20}$ substituted or unsubstituted alkenyl, $(\text{C}_2\text{-C}_4 \text{ alkyleneoxy})_x\text{R}''$, or a substituted or unsubstituted aryl. R' is independently hydrogen, $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl (branched or unbranched), or a substituted or unsubstituted aryl. R'' is hydrogen, a $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl, a $\text{C}_3\text{-C}_{20}$ substituted or unsubstituted alkenyl, a $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkanoyl, or a substituted or unsubstituted aroyl. The integer x ranges from 1-40 and preferably from 2-25.

One organic group is an aromatic group of the formula $\text{A}_y\text{Ar-}$, which corresponds to a primary amine of the formula A_yARNH_2 . In this formula, the variables have the following meanings: Ar is an aromatic radical selected from the group consisting of phenyl, naphthyl, anthracenyl, phenanthrenyl, biphenyl, pyridinyl, and triazinyl; A is a substituent on the aromatic radical independently selected from a functional group described above or A is a linear, branched or cyclic hydrocarbon radical (preferably containing 1 to 20 carbons), unsubstituted or substituted with one or more of those functional groups; and y is an integer from 1 to 5 when Ar is phenyl, 1 to 7 when Ar is naphthyl, 1 to 9 when Ar is anthracenyl, phenanthrenyl, or biphenyl, or 1 to 4 when Ar is pyridinyl, or 1 to 2 when Ar is triazinyl. When A is a $(\text{C}_2\text{-C}_4 \text{ alkyleneoxy})_x\text{R}''$ group, it may be a polyethoxylate group, a polypropoxylate group, or a random or block mixture of the two.

The carbon black may have an attached organic group having a) an aromatic group or a $\text{C}_1\text{-C}_{12}$ alkyl group and b) at least one group of the formula SO_2NR_2 or $\text{SO}_2\text{NR}(\text{COR})$. R may be independently hydrogen, a $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl, a $\text{C}_3\text{-C}_{20}$ substituted or unsubstituted alkenyl, $(\text{C}_2\text{-C}_4 \text{ alkyleneoxy})_x\text{R}'$ or a substituted or unsubstituted aryl; R' is hydrogen, a $\text{C}_1\text{-C}_{20}$ substituted or

unsubstituted alkyl, a C_3 - C_{20} substituted or unsubstituted alkenyl, a C_1 - C_{20} substituted or unsubstituted alkanoyl or substituted or unsubstituted aroyl; and x is from 1 to 40. Aromatic groups include $p\text{-C}_6\text{H}_4\text{SO}_2\text{NH}_2$, $p\text{-C}_6\text{H}_4\text{SO}_2\text{NHC}_6\text{H}_{13}$, $p\text{-C}_6\text{H}_4\text{SO}_2\text{NHCOCH}_3$, $p\text{-C}_6\text{H}_4\text{SO}_2\text{NHCOC}_5\text{H}_{11}$ and $p\text{-C}_6\text{H}_4\text{SO}_2\text{NHCOC}_6\text{H}_5$.

5 Organic groups which may be attached to the silicon-treated carbon black are organic groups substituted with an ionic or an ionizable group as a functional group. An ionizable group is one capable of forming an ionic group in the medium of use. The ionic group may be an anionic group or a cationic group and the ionizable group may form an anion or a cation.

10 Ionizable functional groups forming anions include, for example, acidic groups or salts of acidic groups. The organic groups, therefore, include groups derived from organic acids. When an organic group contains an ionizable group forming an anion, such an organic group may have a) an aromatic group or a C_1 - C_{12} alkyl group and b) at least one acidic group having a pKa of less than 11, or at least one salt of an acidic group having a pKa of less than 11, or a mixture of at least one acidic group having a pKa of less than 11 and at least one salt of an acidic group having a pKa of less than 11. The pKa of
15 the acidic group refers to the pKa of the organic group as a whole, not just the acidic substituent. Preferably, the pKa is less than 10 and more preferably less than 9. The aromatic group or the C_1 - C_{12} alkyl group of the organic group may be directly attached to the carbon black. The aromatic group may be further substituted or unsubstituted, for example, with alkyl groups. The organic group may be a phenyl or a naphthyl group and the acidic group is a sulfonic acid group, a sulfinic acid group, a
20 phosphoric acid group, or a carboxylic acid group. The organic group may also be a substituted or unsubstituted sulfophenyl group or a salt thereof; a substituted or unsubstituted (polysulfo)phenyl group or a salt thereof; a substituted or unsubstituted sulfonaphthyl group or a salt thereof; or a substituted or unsubstituted (polysulfo)naphthyl group or a salt thereof. One substituted sulfophenyl group is a hydroxysulfophenyl group or a salt thereof.

25 Specific organic groups having an ionizable functional group forming an anion are p-sulfophenyl, 4-hydroxy-3-sulfophenyl, and 2-sulfoethyl.

-11-

Amines represent examples of ionizable functional groups that form cationic groups. For example, amines may be protonated to form ammonium groups in acidic media. Preferably, an organic group having an amine substituent has a pK_b of less than 5. Quaternary ammonium groups and quaternary phosphonium groups also represent examples of cationic groups. Preferably, the organic group contains an aromatic group such as a phenyl or a naphthyl group and a quaternary ammonium or a quaternary phosphonium group. The aromatic group is preferably directly attached to the silicon-treated carbon black. Quaternized cyclic amines, and even quaternized aromatic amines, can also be used as the organic group. Thus, N-substituted pyridinium compounds, such as N-methyl-pyridyl, can be used in this regard. Other examples include, but are not limited to, $3-C_3H_4N(C_2H_5)^+X^-$, $C_6H_4NC_3H_5^+X^-$, $C_6H_4COCH_2N(CH_3)_3^+X^-$, $C_6H_4COCH_2(NC_3H_5)^+X^-$, $3-C_3H_4N(CH_3)^+X^-$, $C_6H_4N(CH_3)_3^+X^-$, and $C_6H_4CH_2N(CH_3)_3^+X^-$, where X^- is a halide or an anion derived from a mineral or organic acid.

Alternatively or in combination with the above-described methods of attachment, chemical groups can be attached by reacting with the surface functional groups in the silicon-treated carbon black. For example, the silicon-treated carbon black can be reacted with a trialkoxyalkylsilane, such as octadecyltriethoxysilane, to enhance the compatibility of certain compositions.

The present invention further relates to methods for: improving the jetness, improving the blue tone, improving the platewear, reducing the premix residue, modifying rheological properties, or improving waterfastness, of ink and coating compositions by incorporating therein silicon-treated carbon black.

In a method for improving the jetness of an ink or coating composition, the silicon-treated carbon black preferably contains 0.2 to 5.4 weight percent silicon, based on the weight of the silicon-treated carbon black. In a method for improving the blue tone of an ink or coating composition, the silicon-treated carbon black preferably contains 0.2 to 5.4 weight percent silicon, based on the weight of the silicon-treated carbon black. In a method for improving the platewear of an ink or coating composition, the silicon-treated carbon black preferably contains 0.2 to 25 weight percent silicon, more preferably 0.2 to 10 weight percent, based on the weight of the silicon-treated carbon black. In a method for reducing the pre-mix residue of an ink or coating composition, the silicon-treated carbon black

-12-

preferably contains 0.2 to 25 weight percent silicon, more preferably 0.2 to 10 weight percent, based on the weight of the silicon-treated carbon black. In a method for modifying the rheological properties of an ink or coating composition, the silicon-treated carbon black preferably contains 1 to 25 weight percent silicon, based on the weight of the silicon-treated carbon black. And in a method for improving the waterfastness of an ink or coating composition, the silicon-treated carbon black preferably contains 0.2 to 25 weight percent silicon, based on the weight of the silicon-treated carbon black.

The invention will be further clarified by the following examples, which are intended to be purely exemplary of the invention.

In the examples, below, DBP absorption is measured by the method ASTM D2414. Similarly, CDBP and tinting strength are measured by the methods ASTM D3493 and ASTM D3265.

The nitrogen and external surface area (t-area) is measured following the example preparation and measurement procedure described in ASTM D3037. For this measurement the nitrogen adsorption isotherm is extended up to 0.55 relative pressure. The relative pressure is the pressure (P) divided by the saturation pressure (P₀) (the pressure at which the nitrogen condenses). The adsorption layer thickness (t₁) was then calculated using the relation

$$t_1 = \frac{13.99}{\sqrt{0.034 - \log(P/P_0)}}$$

The volume (V) of nitrogen adsorbed was then plotted against t₁. A straight line was then fitted through the data points for t₁ values between 3.9 and 6.2 Angstroms. The t-area was then obtained from the slope of this line as follows:

$$t - \text{area, m}^2/\text{g} = 15.47 \times \text{slope}$$

Hunter color is measured using Hunter Lab Scan 6000, 10 degree, D 65 CIELAB Color Space instrument manufactured by Hunter Associates in Fairfax, Va. The instrument is calibrated using the

-13-

standard black and white tiles. "L" is the lightness/darkness scale with higher numbers being lighter, "a" is the redness (+)/greenness (-) scale, and "b" is the yellowness (+)/blueness (-) scale. The color values are obtained from a print or draw down of the ink on a paper substrate.

Rub-off is measured using Method A-9 of the Newspaper Association of America. Platewear is measured by placing a portion of the ink on a felt substrate and mechanically rubbing it repeatedly for 6 hours with a brass plate under a standard pressure. The weight loss of the brass plate after 6 hours is rendered as the platewear in grams.

Dispersion classification is made by viewing a 0.1 mil wet film with a transmission microscope at 100x magnification. The level of dispersion (i.e., the quantity and size of the undispersed black) is compared to a standard chart. The scale goes from A to F for the quantity of undispersed agglomerates and from 1 to 6 for size. The higher the number and the lower the letter, the poorer the dispersion quality.

Gloss is measured using ASTM method D523. Steel Bar Laray viscosity is measured using ASTM method D4040. Vertical Glass Plate flow is measured by the distance a 0.5 cc sample of ink travels down a vertical glass plate after the samples are allowed to rest for 0, 30 and 60 minutes prior to standing the plate. Spreadometer properties are measured using a Toyoseiki spreadometer, manufactured by Testing Machines Inc., as described in the Japanese Industrial Standard, Testing Methods for Lithographic and Letterpress Inks (JIS K5701-4.1.2).

Residue is measured by pouring the ink formulations onto a pair of stacked screens with the top and bottom screens being +325M and +625M respectively. The screens are then washed with mineral spirits until the spirits are observed visually to be clear. The screens are then dried in a vented oven at approximately 220°F. The residue on the +325M screen is then weighed to determine +325M residue as a Weight percent of the initial ink formulation.

Example 1

Three carbon blacks were evaluated in a standard low-rub newsink formulation. The blacks are described in Table I below. Sample A is a conventional carbon black and Samples B and C are silicon-treated carbon blacks. The silicon-treated carbon blacks are produced by premixing OMTS with

the carbon black forming feedstock as described above. The three carbon blacks are described in Table I below.

Table I

Sample	% Si based on wt. of carbon black	DBP Absorption (cc/100g)	t-Area (m ² /gm)
A	0.02	1.21	71
B	0.98	118	71
C	5.38	126	71

Each carbon black was pre-mixed in a naphthenic oil-based newsink composition at 20 weight % carbon black loading for 35 minutes using a Dispermat® high speed disk disperser (Getzman GmbH, Germany) at 2300 feet per minute tip speed. The mix was then dispersed in a vertical shot mill containing 1.5 mm steel shot (#550 from Schold Machine Corp., Chicago, IL.) until the dispersion quality, as measured with a NPIRI Grindmeter using ASTM method D1316, contained no 'scratches' and where the 'speckles' disappeared at 20 microns or less. The final dispersion was then reduced to 16 weight % carbon black with the reduction vehicle. The ink composition for all three carbon blacks is presented in Table II below.

Table II

Mix	Ingredients	Weight %
Dispersion (premix)	Hyprene® V2000 Naphthenic Oil	59.44
	Hyprene® V750 Naphthenic Oil	15.60
	Exxprint® 991 (Asphaltic Dispersant)	4.96
	Carbon Black	20.00
Letdown (reduction)	Dispersion	80.00
	Picco® 5140 Hydrocarbon Resin	5.00
	Magie® 47 Naphthenic Oil	5.00
	Hyprene® V2000 Naphthenic Oil	8.66
	Claytone® AF (Bentonite Clay)	1.34

The Hyprene® products were obtained from Ergon Refining, Vicksburg, MS. Exxprint® was obtained from Exxon, Houston, TX. Picco® resin was obtained from Hercules Inc., Wilmington, DE. Magie oil was obtained from Magie Bros., Franklin Park, IL. Claytone® was obtained from Southern Clay Products, Gonzales, TX.

-15-

The results of testing are shown in Table III below. All prints were prepared for evaluation by printing to an optical density of 1.0 on newsprint using an RNA 52 Printability Tester manufactured by Research North America, Cherry Hill, NJ.

Table III

Property/Sample	A	B	C
Dispersion (4 Scratch/10 Scratch/Speckles)			
2 minutes - microns	0/0/40	0/0/30	6/0/50
4 minutes - microns	0/0/22	0/0/21	0/0/35
6 minutes - microns	0/0/16	0/0/17	0/0/22
8 minutes - microns	--	--	0/0/19
Premix Residue (% + 325 mesh)	3.05	1.55	1.05
Final Residue (% + 325 mesh)	0.010	0.008	0.008
3 hour ruboff (optical density)	0.21	0.20	0.20
Platewear (grams/6 hours)	0.0217	0.0195	0.0176
Hunter Color			
L	38.77	36.79	37.94
a	1.40	1.35	1.36
b	6.32	5.91	6.18

The premix residue was lower for the silicon-treated carbon blacks. The silicon-treated carbon blacks showed improved jetness and bluer tone as measured by the lower L and b values for the Hunter Color of Samples B and C relative to Sample A. The silicon-treated carbon blacks also showed improved platewear over Sample A.

Example 2

Three carbon blacks were evaluated in a standard aqueous acrylic flexographic formulation. Sample D was a conventional carbon black and Samples E and F were silicon-treated carbon blacks.

-16-

The carbon blacks are described in Table IV below. The silicon-treated carbon blacks were produced as described earlier by premixing OMTS with the carbon black producing feedstock.

Table IV

Sample	% Si based on wt. of carbon black	DBP Absorption (cc/100g)	t-Area (m ² /gm)
D	0.06	102	95
E	1.30	106	103
F	5.50	114	95

Each carbon black was pre-mixed in an aqueous acrylic flexographic ink composition at 24.4 weight % carbon black for 30 minutes using a Dispermat® high speed disk disperser at 2300 feet per minute tip speed. The pre-mix was then dispersed in a horizontal shot mill (Model M-50 Eiger Machinery, Bensonville, IL) with 2 mm stainless steel shot. 150 grams of the ink composition was recycled through the mill for 45 minutes at a flow rate of approximately 200 grams per minute. 10 grams of material was removed at 15 minute intervals and reduced to 9.76 weight percent carbon black with additional water and resin prior to color and dispersion evaluation. The reduction was performed by shaking the dispersion, water and resin for 15 minutes on a paint shaker (Model 5400 Red Devil Equipment, Union, N.J.). The ink composition for all three blacks is presented in Table V below.

Table V

Mix	Ingredients	Weight %
Dispersion (premix)	Joncryl® 61 Acrylic resin Joncryl® 62 Acrylic resin Dymisol® 200 (polyethylene glycol) Byk 020 (polysiloxane defoamer) Distilled Water Carbon black	31.5 10.0 5.0 0.5 28.6 24.4
Letdown (Reduction)	Dispersion Joncryl® 61 Acrylic resin Distilled water	40.0 55.2 4.8

Joncryl® Acrylic resin was obtained from S.C. Johnson, Racine, WI. Dymisol Acrylic resin was obtained from Henkel Corp., Kankakee, IL., Byk 020 was obtained from Byk Chemie, Wallingford, Ct.

-17-

The results of the testing are shown in Table VI below.

Table VI

Property/Sample	D	E	F
Dispersion Classification			
15 minutes	2C	1E	1E
30 minutes	1D	1C	1C
45 minutes	1C	1B	1B
Final Residue (% + 325 mesh)	0.0015	0.0010	0.0003
Hunter Color			
15 minutes			
L	11.29	10.36	11.16
a	-0.48	-0.51	-0.54
b	-3.18	-3.30	-3.34
30 minutes			
L	11.87	11.52	11.22
a	-0.50	-0.63	-0.58
b	-3.19	-3.33	-3.41
45 minutes			
L	11.49	11.28	10.33
a	-0.48	-0.59	-0.55
b	-3.14	-3.44	-3.41

The silicon-treated carbon blacks showed better, i.e., faster, dispersion compared to Sample D.

The silicon-treated carbon blacks were also darker and bluer as indicated by the lower Hunter 'L' and more negative Hunter 'b' values.

Example 3

The carbon black Samples D, E and F were evaluated in a standard heat set gloss ink formulation prepared on a three-roll mill.

The carbon black samples were prepared for grind on a three roll mill (Kent Machine Works, Brooklyn, NY). A premix consisting of 105 grams of carbon black and 245 grams of grind masterbatch (consisting of 9 parts of LV - 3427XL heatset grinding vehicle obtained from Lawter International, Northbrook, IL., to 1 part Magie® naphthenic oil) was prepared in the Dispermat running at 5000 rpm for 30 minutes. This mixture, 50 g, was ground on the Kent three roll mill running at 70°F. Samples were let down by mixing with an equal amount of the grind masterbatch and then applied to a NIPRI production grindmeter G-2 for evaluation of grind. Additional passes were made if the grind gauge

-18-

reading was above 20. The finished ink was produced by mixing the milled material with an equal weight of reduction masterbatch (3 parts LV-3427XL; 12 parts LV 6025, a reduction vehicle obtained from Lawter International, Northbrook, IL; 5 parts MAGIESOL 47) and passing one time through the three roll mill.

5 Fineness of grind data for samples D, E, and F. and viscosity measurements for the resulting inks are shown in Table VII below. The numbers in the grind data table are in microns as measured on a G-2 grind gauge and indicate the level where 5 defect grains are detected on the grind gauge. Designations > 50 indicate hangback or separation of the carbon black from the grind vehicle.

10 Optical properties for inks made from Samples D, E and F were determined from prints made using the RNA-52 printability tester. These values are shown in Table VIII.A and Table VIII.B. Values for 1 and 2 micron film thickness were calculated from regression of the data from the prints having a range of film thicknesses. The higher Si-content sample dispersed somewhat easier than the sample with no added silicon on the three roll mill.

15 The viscosity measurements in Table VII show the effect of increasing Si-content in this ink formulation. Under conditions of low shear (vertical glass plate flow), Sample F, having the highest Si-content, showed significantly lower flow than either Sample D or E. Once shear is applied to these inks the rheological differences become smaller. The spreadometer slope (indicator of flowability at higher shear) is greater for Sample F, just the opposite of that observed for vertical glass plate flow.

Table VII

Properties/Sample	D	E	F
Carbon Black Properties			
Silicon content (% of carbon black)	0.06	1.30	5.50
DBP	102	106	114
t-area (m ² /g)	95	103	95
Ink Preparation			
Grinding Base (5 scr/10 scr/sand)			
Three roll mill			
1 pass	> 50	> 50	> 50
2 pass	> 50	> 50	> 50
3 pass	> 50	> 50	0/0/46
4 pass	0/0/42	0/0/50+	0/0/30
5 pass	0/0/32	0/0/42	0/0/26
6 pass	0/0/24	0/0/30	0/0/17
7 pass	0/0/25	0/0/23	
8 pass	0/0/24	0/0/21	
Ink Properties			
Steel Bar Laray Viscosity			
Viscosity (poise at 2500 s ⁻²)	61.9	67.0	63.2
Yield Value (dyne/cm at 2.5 s ⁻¹)	695	590	621
Vertical Glass Plate Flow (mm)			
No Setting			
20 minutes	70	75	45
40 minutes	85	89	51
60 minutes	99	100	55
30 minutes setting			
20 minutes	50	46	21
40 minutes	65	60	31
60 minutes	75	71	36
60 minutes setting			
20 minutes	45	40	19
40 minutes	57	52	27
60 minutes	69	61	34
Spreadometer Properties			
Slope (mm)	8.3	8.1	9.7
Interceptor (mm)	27.7	25.8	24.7
Yield Value (dyne/cm ²)	121.7	120.1	121.7

Table VIII.A Optical Properties of a 1 micron film made from Samples D-F

SAMPLE	OD	L	a	b	Gloss 60°
D	1.23	28.4	1.18	3.48	40.9
E	1.23	27.8	1.21	3.41	38.7
F	1.28	27.7	1.35	4.00	38.3

Table VIII.B Optical Properties of a 2 micron film made from Samples D-F

SAMPLE	OD	L	a	b	Gloss 60°
D	2.04	8.2	0.54	0.45	46.8
E	2.08	7.9	0.80	0.74	43.7
F	1.80	12.7	1.23	2.49	44.1

It is seen that at a relatively high level of silicon treatment, 5.5% Si by weight, there is a significant decrease in flowability at low shear (low values of vertical glass plate flow) and a significant increase in flowability at higher shear (high values of slope of spreadometer properties). Thus, the silicon-treated carbon black can be used as a rheological modifier.

Example 4

Inkjet inks were prepared from silicon-treated carbon blacks G and H (described below) having attached $\text{CH}_3(\text{NC}_5\text{H}_5)^+$ groups. Silver nitrite (2.85 g) was added to a solution of 3.1 g of N-(4-aminophenyl)pyridinium chloride in 100 g of water and the mixture was stirred at 70-80°C for one hour. The mixture was filtered after stirring overnight at room temperature. Each of the two silicon-treated carbon blacks (10 g @) were separately added to 35 grams of the filtrate, and about 55 grams of water was added. The resulting mixtures were heated to 70°C and 0.5 gram of 37% aqueous HCl was added. The dispersions were stirred at 70°C for 1.5 hours and at room temperature overnight. Thus, mixtures were formed of silicon-treated carbon blacks having attached $\text{C}_6\text{H}_4(\text{NC}_5\text{H}_5)^+$ groups and water.

Sample G is a silicon-treated carbon black containing 1.6% silicon that has a t-area of 119 m²/g and a DBP absorption value of 115 cc/100 g. Sample H is a silicon-treated carbon black that contains 5.2% silicon and has a t-area of 125.5 m²/g and a DBP adsorption of 105 cc/100 g. The samples were produced by premixing OMTS with the carbon black producing feedstock, as discussed above.

Inks were prepared by diluting the dispersions with water so the solids contents were 3-7 weight % as shown below. The inks were drawn down as a film using a 3 Mil Bird applicator and allowed to dry for 10 minutes. A portion of the image was rinsed with a stream of water until no additional ink was washed off. After drying at room temperature, the optical densities of the washed and unwashed

portions were measured to determine the percent of waterfastness. These results are summarized in Table IX.

Mean particle diameters and the maximum particle diameters were measured using a MICROTRAC Ultrafine Particle Analyzer from Leeds & Northrup Co., St. Petersburg, FL.

5 Surface tensions of the inks were measured using a CSC DU NUOY Tensiometer, No. 70535 from CSC Scientific Co., Inc., Fairfax, Va. using the ASTM D1331 and D-1590 procedures.

Viscosities were measured using a No. 1 and No. 2 shell cup from Norcross Corporation, Newton, MA using ASTM procedure D4212.

Table IX

Run	Sample	Mean particle size, μ	Maximum particle size, μ	Solids Wt. %	Surface tension, dynes/ cm	Vis- cosity, cP	Optical density before washing	Optical density after washing	Water- fastness (% re-tained)
1	G	0.23	0.58	3	—	—	1.51	1.48	98
2	G	0.23	0.58	5	73.8	1.5	1.63	1.57	96
3	G	0.23	0.58	7	—	—	1.66	1.54	93
4	H	0.24	0.69	3	—	—	1.49	1.45	97
5	H	0.24	0.69	5	74.1	1.5	1.68	1.61	95
6	H	0.24	0.69	7	—	—	1.69	1.61	95

These results show that the silicon-treated carbon blacks are useful in inkjet inks, and that prints made from these inks have excellent waterfastness.

20 Other embodiments of the present invention will be apparent to those skilled in the art from consideration of the specification and practice of the invention disclosed herein. It is intended that the specification and examples be considered as exemplary only, with a true scope and spirit of the invention being indicated by the following claims.

What is claimed is:

1. An ink composition comprising silicon-treated carbon black.
2. The ink composition of claim 1, wherein at least a portion of the silicon-treated carbon black is silicon-treated carbon black having at least one organic group attached.
- 5 3. The ink composition of claim 1, further comprising carbon black having at least one organic group attached, or mixtures of carbon black having at least one organic group attached and silicon-treated carbon black having at least one organic group attached.
4. The ink composition of claim 1, further comprising untreated carbon black.
5. The ink composition of claim 1, wherein the silicon-treated carbon black is present in
10 an amount up to 60% by weight of the composition.
6. The ink composition of claim 1, wherein aggregates of the silicon-treated carbon black have silicon-containing regions primarily at the surface.
7. The ink composition of claim 1, wherein aggregates of the silicon-treated carbon black have silicon-containing regions dispersed throughout.
- 15 8. The ink composition of claim 1, wherein the silicon-treated carbon black contains from about 0.1 to about 25 wt.% silicon, based on the weight of the silicon-treated carbon black.
9. The ink composition of claim 8, wherein the silicon-treated carbon black contains from about 0.2 to about 10 wt.% silicon, based on the weight of the silicon-treated carbon black.
10. The ink composition of claim 9, wherein the silicon-treated carbon black contains from
20 about 0.2 to about 5.4 wt.%, based on the weight of the silicon-treated carbon black.
11. The ink composition of claim 1, where the composition is aqueous.
12. The ink composition of claim 1, where the composition is non-aqueous.
13. A coating composition comprising silicon-treated carbon black.
14. The coating composition of claim 13, wherein at least a portion of the silicon-treated
25 carbon black is silicon-treated carbon black having at least one organic group attached.

15. The coating composition of claim 13, further comprising carbon black having at least one organic group attached, or mixtures of carbon black having at least one organic group attached and silicon-treated carbon black having at least one organic group attached.

16. The coating composition of claim 13, further comprising untreated carbon black.

5 17. The coating composition of claim 13, wherein the silicon-treated carbon black is present in an amount up to 60% by weight of the composition.

18. The coating composition of claim 13, wherein aggregates of the silicon-treated carbon black have silicon-containing regions primarily at the surface.

10 19. The coating composition of claim 13, wherein aggregates of the silicon-treated carbon black have silicon-containing regions dispersed throughout.

20. The coating composition of claim 13, wherein the silicon-treated carbon black contains from about 0.1 to about 25 wt.% silicon, based on the weight of the silicon-treated carbon black.

21. The coating composition of claim 20, wherein the silicon-treated carbon black contains from about 0.5 to about 10 wt.% silicon, based on the weight of the silicon-treated carbon black.

15 22. The coating composition of claim 20, wherein the silicon-treated carbon black contains from about 0.2 to about 5.4 wt.%, based on the weight of the silicon-treated carbon black.

23. The coating composition of claim 13, where the composition is aqueous.

24. The coating composition of claim 13, where the composition is non-aqueous.

20 25. An aqueous ink jet ink composition comprising an aqueous vehicle and silicon-treated carbon black.

26. A non-aqueous ink jet ink composition comprising a nonaqueous vehicle and silicon-treated carbon black.

27. A method for improving the jetness of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

25 28. The method of claim 27, wherein said silicon-treated carbon black contains 0.2 to 5.4 wt.% silicon, based on the weight of the silicon-treated carbon black.

-24-

29. A method for improving the blue tone of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

30. The method of claim 29, wherein said silicon-treated carbon black contains 0.2 to 5.4 wt. % silicon, based on the weight of the silicon-treated carbon black.

5 31. A method for improving the platewear of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

32. The method of claim 31, wherein said silicon-treated carbon black contains 0.2 to 25 wt. % silicon, based on the weight of the silicon-treated carbon black.

10 33. A method for reducing the premix residue of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

34. The method of claim 33, wherein said silicon-treated carbon black contains 0.2 to 25 wt. % silicon, based on the weight of the silicon-treated carbon black.

35. A method for modifying rheological properties of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

15 36. The method of claim 35, wherein said silicon-treated carbon black contains 1 to 25 wt. % silicon, based on the weight of the silicon-treated carbon black.

37. A method for improving the waterfastness of an ink or coating, comprising the step of incorporating in said ink or coating a silicon-treated carbon black.

20 38. The method of claim 37, wherein said silicon-treated carbon black contains 0.2 to 25 wt. % silicon, based on the weight of the silicon-treated carbon black.

39. The ink composition of claim 2, wherein said attached organic group is selected from an ionic group, an ionizable group, or mixtures thereof.

25 40. The ink composition of claim 39, wherein said attached organic group is selected from sulfonic acid or salts thereof, carboxylic acid or salts thereof, a quaternary ammonium group, SO_2NR_2 , or $\text{SO}_2\text{NR}(\text{COR})$, where R is independently hydrogen, a $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl, a $\text{C}_3\text{-C}_{20}$ substituted or unsubstituted alkenyl, $(\text{C}_2\text{-C}_4 \text{ alkyleneoxy})_x\text{R}'$ or a substituted or unsubstituted aryl, and R' is hydrogen, a $\text{C}_1\text{-C}_{20}$ substituted or unsubstituted alkyl, a $\text{C}_3\text{-C}_{20}$ substituted or unsubstituted

alkenyl, a C_1 - C_{20} substituted or unsubstituted alkanoyl or substituted or unsubstituted aroyl; and x is from 1 to 40.

41. The ink composition of claim 39, where said attached organic group is $p\text{-C}_6\text{H}_4\text{SO}_3\text{Na}$.

42. The ink composition of claim 39, where said attached organic group is
5 $p\text{-C}_6\text{H}_4\text{CO}_2\text{H}$.

43. The ink composition of claim 39, where said attached organic group is selected from $\text{C}_6\text{H}_4\text{NC}_3\text{H}_5^+\text{X}^-$ or $\text{C}_6\text{H}_4\text{N}(\text{CH}_3)_3^+\text{X}^-$, where X^- is a halide or an anion derived from a mineral or organic acid.

44. The ink composition of claim 39, where said attached organic group is selected from
10 $\text{C}_6\text{H}_4\text{SO}_2\text{NH}_2$ or $\text{C}_6\text{H}_4\text{SO}_2\text{NH}(\text{COCH}_3)$.

45. The coating composition of claim 2, wherein said attached organic group is selected from an ionic group, an ionizable group, or mixtures thereof.

46. The coating composition of claim 45, wherein said attached organic group is selected from sulfonic acid or salts thereof, carboxylic acid or salts thereof, a quaternary ammonium group, SO_2NR_2 , or $\text{SO}_2\text{NR}(\text{COR})$, where R is independently hydrogen, a C_1 - C_{20} substituted or
15 unsubstituted alkyl, a C_3 - C_{20} substituted or unsubstituted alkenyl, $(\text{C}_2\text{-C}_4 \text{ alkyleneoxy})_x\text{R}'$ or a substituted or unsubstituted aryl, and R' is hydrogen, a C_1 - C_{20} substituted or unsubstituted alkyl, a C_3 - C_{20} substituted or unsubstituted alkenyl, a C_1 - C_{20} substituted or unsubstituted alkanoyl or substituted or unsubstituted aroyl; and x is from 1 to 40.

47. The coating composition of claim 45, where said attached organic group is
20 $p\text{-C}_6\text{H}_4\text{SO}_3\text{Na}$.

48. The coating composition of claim 45, where said attached organic group is
 $p\text{-C}_6\text{H}_4\text{CO}_2\text{H}$.

49. The coating composition of claim 45, where said attached organic group is selected from
25 $\text{C}_6\text{H}_4\text{NC}_3\text{H}_5^+\text{X}^-$ or $\text{C}_6\text{H}_4\text{N}(\text{CH}_3)_3^+\text{X}^-$, where X^- is a halide or an anion derived from a mineral or organic acid.

-26-

50. The coating composition of claim 45, where said attached organic group is selected from $\text{C}_6\text{H}_4\text{SO}_2\text{NH}_2$ or $\text{C}_6\text{H}_4\text{SO}_2\text{NH}(\text{COCH}_3)$.

51. A colorant comprising a silicon-treated carbon black.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/08854

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09D11/00 C09D11/02 C09C1/56

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 1 213 186 A (J. M. HUBER) 18 November 1970 see claim 1	51
P,X	WO 96 37547 A (CABOT CORP.) 28 November 1996 cited in the application	51
A	see page 6, line 26 - page 17, line 17	1,2, 39-50
P,X	WO 97 10291 A (CABOT CORP.) 20 March 1997 cited in the application	51
A	see page 5, last paragraph	1,8-10, 20-22, 28-30, 34,36,38
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "Z" document member of the same patent family

Date of the actual completion of the international search

15 October 1997

Date of mailing of the international search report

06.11.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Bellinghen, I

INTERNATIONAL SEARCH REPORT

Intern 1st Application No

PCT/US 97/08854

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 96 37546 A (CABOT CORP.) 28 November 1996	51
A	see page 6, line 9 - page 16, paragraph 1 ---	2,39-50
X	DATABASE WPI Week 8817 Derwent Publications Ltd., London, GB; AN 88-116672 XP002043688 & JP 63 063 755 A (DAINICHISEIKA COLOR & CHEM. MFG.; NIPPON OILS & FATS CO.) , 22 March 1988 see abstract ---	13,51
A	DE 19 48 443 A (DEGUSSA) 8 April 1971 see claim 1 ---	51
A	EP 0 675 175 A (MERCK PATENT) 4 October 1995 see claims 1,8 ---	13,51
A	US 2 793 100 A (DEGUSSA) 21 May 1957 see column 1, line 35-40; claim 1 ---	2,14,51
P,A	WO 96 18688 A (CABOT CORP.) 20 June 1996 cited in the application see page 10, line 24-35 see page 11, line 26-30 -----	2,14, 39-51

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/08854

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 1213186 A	18-11-70	FR 1580906 A	12-09-69
WO 9637547 A	28-11-96	AU 6540396 A	11-12-96
WO 9710291 A	20-03-97	AU 7157596 A	01-04-97
WO 9637546 A	28-11-96	AU 5867396 A	11-12-96
DE 1948443 A	08-04-71	FR 2062679 A	25-06-71
		US 3660132 A	02-05-72
EP 675175 A	04-10-95	CZ 9500789 A	15-11-95
		DE 19503906 A	05-10-95
		FI 951502 A	01-10-95
		JP 7268240 A	17-10-95
US 2793100 A	21-05-57	NONE	
WO 9618688 A	20-06-96	AU 4378496 A	03-07-96
		AU 4472096 A	03-07-96
		EP 0799281 A	08-10-97
		EP 0797637 A	01-10-97
		NO 972736 A	13-08-97
		NO 972737 A	08-08-97
		WO 9618696 A	20-06-96
		US 5672198 A	30-09-97
		ZA 9510659 A	30-05-96
		ZA 9510664 A	09-07-96

This Page Blank (uspto)